Serial No.: 10/627,238 Filed: July 24, 2003

Amendment in Response to April 19, 2007 Office Action

October 19, 2007

Page 2

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

- 1. (currently amended) A process for applying a <u>water-based</u> catalyst ink onto a substrate, said process comprising the steps:
  - (a) coating a substrate with [[a]] the water-based catalyst ink under conditions of controlled humidity and temperature to form a deposited catalyst ink on said substrate, wherein said catalyst ink comprises an electrocatalyst, an ionomer and water;
  - (b) leveling the deposited catalyst ink under conditions of controlled humidity and temperature to form a catalyst-coated substrate; and
  - (c) drying the catalyst-coated substrate at an elevated temperature

wherein the coating step (a) occurs in a coating compartment and the leveling step (b) occurs in a leveling compartment for a period of 1 to 10 minutes.

- 2. (original) The process according to claim 1, wherein said catalyst ink further comprises an organic solvent.
- 3. (previously amended) The process according to claim 1, wherein said catalyst ink further comprises a surfactant with a vapor pressure between 1 and 600 Pascal.

Serial No.: 10/627,238 Filed: July 24, 2003

Amendment in Response to April 19, 2007 Office Action

October 19, 2007

Page 3

4. (previously amended) The process according to claim 1, wherein the substrate is

selected from the group consisting of a hydrophobic polymer film, a transfer tape

material, a paper-based material, a decal substrate, a metal substrate tape, an ionomer

membrane, a carbon paper, a carbon fiber substrate, a carbon cloth, a woven or nonwoven

carbon mesh, a needled felt, a knitted fabric, and a carbon felt.

5. (original) The process according to claim 4, wherein said substrate is present in

individual sheet or in continuous roll form.

6. (previously amended) The process according to claim 1, wherein the humidity in the

coating compartment is maintained at 60 to 100 % relative humidity and a temperature in

the range of 10 to 60°C, and the humidity in the leveling compartment is maintained at 60

to 100% relative humidity and at a temperature in the range of 10 to 60°C.

7. cancelled.

8. (previously amended) The process according to claim 1, wherein the drying step (c) of

the catalyst ink. is perfumed at a temperature in the range of 40 to 150°C for 1 to 10

minutes.

9. cancelled.

10. cancelled.

11. (withdrawn-previously amended) A catalyst-coated membrane comprising the

catalyst-coated substrate produced according to the process of claim 1.

12. (withdrawn-previously amended) A catalyst-coated gas diffusion substrate

comprising the catalyst-coated substrate produced according to the process of claim 1.

Serial No.: 10/627,238 Filed: July 24, 2003

Amendment in Response to April 19, 2007 Office Action

October 19, 2007

Page 4

13. (withdrawn-previously amended) A catalyst-coated polymer film comprising the catalyst-coated substrate produced according to the process of claim 1.

14. (withdrawn-previously amended) A membrane-electrode-assembly comprising the catalyst-coated membrane of claim 11.

15. (withdrawn-previously amended) A membrane-electrode-assembly comprising the catalyst-coated gas diffusion substrate of claim 12.

16. (withdrawn-previously amended) A membrane-electrode-assembly comprising the catalyst-coated polymer film of claim 13.

17. (withdrawn) A method of using the membrane-electrode-assembly of claim 14, comprising operating a PEMFC or DMFC fuel stack, wherein said fuel stack is comprised of said membrane-electrode assembly.

18. (withdrawn) A method of using the membrane-electrode-assembly of claim 15, comprising operating a PEMFC or DMFC fuel stack, wherein said fuel stack is comprised of said membrane-electrode assembly

19. (withdrawn) A method of using the membrane-electrode-assembly of claim 16, comprising operating a PEMFC or DMFC fuel stack, wherein said fuel stack is comprised of said membrane-electrode assembly.

20. (currently amended) The process according to claim 1, wherein the coating of the substrate is applied by screen printing, stencil printing, offset printing, transfer printing, doctor blading, brushing, or spraying, or other known coating techniques.

Serial No.: 10/627,238 Filed: July 24, 2003

Amendment in Response to April 19, 2007 Office Action

October 19, 2007

Page 5

21. (currently amended) The process according to claim 1, wherein the coating step (a) and the <u>levelling leveling step</u> (b) are performed in one <u>large</u> compartment comprising a coating section and a <u>levelling leveling section</u>.